



# Wood Wax

For untreated and waxed furniture, chests, carvings, sculptures and picture frames.



1 liter is sufficient for approx. 10 m<sup>2</sup> per coat



suitable for children's toys



can be painted over after 8–12 hours



suitable for internal use

## Characteristics:

Brings out the structure and grain of the wood. Subsequent polishing produces a beautiful lustre with a special smoothness. Has a water-repellent and moisture-regulating effect. Resists household cleansers. The dried coat complies with DIN EN 71, part 3 (safety of toys), and DIN 53160 (saliva and sweat resistance), and DIN 68861-1C (exposure to chemicals).

## Areas of Application:

For decorative treatment of untreated wood and for maintaining waxed surfaces in indoor areas, such as furniture, shelves, wall and ceiling cladding, or toys. Unsuitable for floors.

## Technical Data:

Density at 20 °C: approx. 0,850 g/cm<sup>3</sup> (DIN 51757)

## Colour shades:

colourless

## Container sizes:

250 ml and 750 ml

## Storage:

Store in well-sealed original containers in a cool place protected from frost. Can be stored for 5 years in original sealed containers.

## Disposal:

Recommended waste code according to the European Waste Directory: 08 01 11 (the final commitment must be made in coordination with the regional waste utility).

## Water hazard class:

Slightly hazardous for water

## Safety precautions:

Even when working with low-polluting products the usual safety measures should be complied with. Store out of the reach of children. Wear suitable protective clothing. Ensure there is a good supply of air during work and drying. If product comes in contact with the eyes or skin, wash thoroughly with water immediately. Do not allow product to find its way into the sewage system, surface waters, or groundwater. Please refer to the safety data sheet for more information.

## PROCESSING

### Preparation:

The wood surface must be clean, dry and free of oil and grease. Sand with 200/240 grit and remove dust thoroughly.

### Processing:

(Surface temperature > 15 °C, residual moisture 8–12 %) Shake CLOU Wood Wax well before use. Do not use under 15 °C. Apply thinly and uniformly using a soft brush or cotton cloth in the direction of the wood structure. In cases of very absorbent substrates a second coat is necessary. Do this after allowing to dry and sanding with 240/280 grit.

### Subsequent treatment:

For a special smoothness with a nice feel and attractive lustre, polish after drying with CLOU Wax Polishing Brush or brush with horsehair bristle.

### Coverage:

1 liter is sufficient for approx. 10 m<sup>2</sup> per coat

### Drying:

(at 20 °C and 50 % relative humidity)

Can be worked after 8–12 hours. Ensure there is a good supply of ventilation during work and drying.

### Cleaning the work equipment:

Clean the used brushes thoroughly with CLOU Universal Colour-Solver or CLOU EV-Thinner immediately after use. Properly dispose of any residues from cleaning.

### Special Instructions:

Oil-soaked cloths can potentially ignite spontaneously. For this reason, soak them with water after use and spread them out to dry in the open. The product itself cannot ignite spontaneously.

---

## Technical Information

Date July 2017

This information is of a non-binding nature and is based solely on our tests and experience. As we cannot influence the on-site application and use, no liability is expressed by the contents of this data sheet. It is the user's own responsibility to adapt the processing instructions to the prevailing working conditions and to test the suitability of the products for the

intended use by carrying out a process test where necessary. Our products are manufactured for professional users with a sound basic knowledge of using lacquers, glazes and stains. If unsure, our applications and laboratory technicians can advise to the best of their knowledge. The advice is non-binding unless confirmed in writing. Naturally we guarantee the quality of our products. Our general terms of sale and delivery apply. This information will become invalid when a new edition is released.