

CARVER s.r.l.

Via Giovanni XXIII, 36 - 20090 Rodano (MI) ITALY

Tel. 02.95.00.17.1 - Fax 02.95.320.921

internet: www.carver.it - E-mail: carver@carver.it

TECHNICAL LEAFLET

rev. 08 of 25/05/00

STUCCO RS**code FO2040****TECHNICAL DATA** (with room temperature of +20°C and 65% of relative air humidity)

Viscosity	25 " Ford cup 8
Specific weight	0.91 ± 0,01
Dust dry	30 min.
Over-varnishing after	2 hr.
Dry for sanding after	1 hr.
Completely dry after	2 hr.

DESCRIPTION

STUCCO RS is a monocomponent transparent binder on solvent base to prepare a quick-drying and easily sanded filler for filling and smoothing parquet.

DIRECTIONS FOR USE

Sand the floor with coarse- and medium-grained sandpaper then prepare the filler, blending STUCCO RS and the necessary quantity of sawdust from the sanding, to obtain an homogeneous mixture. Spread it quickly using a wide, rustproof metal spatula (American spatula), pushing as much filler as possible into the cracks.

After drying, which normally requires 1 hour, smooth using fine sandpaper, vacuum and wipe up dust carefully, then apply one of our solvent-based finish cycles.

WARNINGS

Do not apply at a temperature below +15 °C. The product itself, before being applied, should reach the room temperature.

To thin, use our DILUENTE V3a thinner.

Clean tools with our DILUENTE LAVAGGIO washing diluent.

Do not dispose of residual product on ground or down drains!

If stored cool and dry, in the original unopened package, the product will keep for at least 12 months.

N.B. The information contained in this technical leaflet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.