



TECHNICAL DATA SHEET

rev. 00 25/05/2005

EXTEROL 040 (impregnating oil for outdoors)

code SO8501

TECHNICAL DATA

(based on room temperature of +23°C and 65% of relative air humidity)

Appearance	opalescent brown liquid
Viscosity	12" F4 ± 1" F4
Specific weight	0.85 ± 0.01
Superficial drying	2 - 4 hours
Recoating after / within	6 / 24 hours
Cautious foot traffic after	24 - 48 hours
Complete drying	10 - 15 days
Coverage (per coat) ♦	15 - 30 m ² /litre
VOC	60% ± 1%

♦ depending on the wood species, on how abrading is effected and on the quantity of absorbed product

DESCRIPTION

A natural resin- and oil-based product from the GREEN LINE series, specially engineered for **outdoor** wood protection. It is suitable both for the treatment of raw wood and the restoring of previously treated wood articles. Recommended for professional as well as for do-it-yourself use, EXTEROL 040 is available in many versions: transparent colourless or transparent coloured (white, yellow, green, blue, red, douglas, ebony, mahogany, walnut, walnut mansoniana, rosewood, oak, teak).

Standard packaging: 2.5-lt can. Ready-to-use product.

DIRECTIONS

Sand the surface with 100÷120-grit abrasives, removing all wax, oil or existing finish, then clean thoroughly the surface from all dust. Agitate well the EXTEROL 040 can, to permit the adequate dispersion of the opacifying matter and the pigments (if coloured version). Apply the product by brush, cloth or pad. After few minutes, it is necessary to rub the surface with a cloth or a pad, to help penetration into the wood pores and to remove exceeding oil. After 1 to 2 hours polish with soft felt.

After 6 and within 24 hours, a second coat can be applied, according to the described procedure. No abrading is required except after 48 hours..

NOTICE

- Apply at a temperature between +15° and +35°C. Allow the product and the support to reach at least the temperature of +15° C before application.
- The support to be treated should have a humidity content inferior to 15%.
- Do not leave excess product on the surface. At the end of the treatment, the oil must have been completely absorbed by the wood.
- The oiled wood must not come in contact with water for at least 48 hours after the application.
- For thinning EXTEROL 040 (if necessary) and cleaning the tools, use Carver DILUENTE LINOLUX.
- **Soak used rags and cloths in water immediately after use to prevent spontaneous combustion.**

Dispose of excess product and empty containers properly.

If the original unopened container is stored in a cool and dry place, the product will keep for at least 12 months.

The information contained in this technical data sheet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.