

**CARVER** s.r.l.

Via Giovanni XXIII, 36 - 20090 Rodano (MI) ITALY  
Tel. 02.95.00.17.1 - Fax 02.95.320.921  
internet: www.carver.it - E-mail: carver@carver.it

AZIENDA CON SISTEMA QUALITÀ  
CERTIFICATO DA DNV  
**UNI EN ISO 9002**

**TECHNICAL DATASHEET**

rev. 00 of 18/10/01

**STUCCO AQ**

code FO6500

**TECHNICAL DATA***(based on room temperature of +23°C and 65% relative air humidity)*

Viscosity	50" Ford cup 8
Specific weight	1.01 ± 0,01
pH	6.5 ± 0.5
Dry to touch	20 min.
Recoat after	1 h
Sanding after	2-3 h.
Completely dry	12 h.
Yield	8-12 m <sup>2</sup> /litre

**DESCRIPTION**

Single-component, **solvent-free** bonding agent to prepare a filler for wood floors and other surfaces. It gives a filler of the same color of the wood and does not cause any toning. STUCCO AQ can be coated over with waterborne and solvent-based finishes as well as with impregnating oils.

**APPLICATION**

Sand the floor with coarse and medium grained abrasive.

Mix STUCCO AQ with dust from the final sanding to form an homogeneous paste. Spread it quickly with a stainless, wide spatula (American spatula), pushing as much filler as possible into the cracks.

After drying, which normally requires 2-3 hours, sand or screen with fine abrasive, then vacuum and tack (with an antistatic cloth) thoroughly.

Should the filler shrink excessively in the largest cracks (over 2 mm), do the filling once again as described above.

Go on with the finishing or the impregnation.

**IMPORTANT!**

Do not apply at temperatures below +15° C. Allow the product to reach room temperature before application.

Use water for any possible thinning and for the cleaning of the tools.

**Protect from freezing!**

**Dispose of excess product and empty containers properly.**

**If the original unopened container is stored in a cool dry place, away from direct sun light, the product will keep for at least 12 months.**

**The information contained in this technical datasheet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.**